

Fluorine-based Organic Piezoelectric Materials [V series]

Under Development

Summary

Our fluorine-based organic piezoelectric materials are made of polymeric materials that have piezoelectric properties. They are particularly suitable for mechanical to electrical conversion (sensor) applications because they have a lower dielectric constant and a higher voltage output factor (g constant) than ceramic piezoelectric materials (PZT, etc.). They also have excellent flexibility, making it possible to attach it to curved surfaces.




Features

- Flexible, lightweight, and excellent workability
- Excellent impact resistance, water resistance, heat resistance (<120℃), and chemical stability
- Superior piezoelectricity and clear characteristics in 33 directions $(d_{33} >> d_{31}, d_{32})$ in comparison to general PVDF materials
- Acoustic impedance is close to that of organisms and water
- Low environmental impact due to the absence of lead

Applications

- Sensors: vibration sensors, acceleration sensors, strain gauges, pulse/heart rate sensors
- Acoustics: speakers, microphones, electronic instrument pickups
- Ultrasonic: medical ultrasonic probes, flaw detector, hydrophone
- Others: energy harvesting, etc.




FUJI CERAMICS CORPORATION


Head Office 2320-11 Yamamiya, Fujinomiya-shi,Shizuoka 418-0111, Japan Web: <u>https://www.fujicera.co.jp/en/</u>


Basic Characteristics

Item	Unit	V-1
K ₃₁	%	7.7
K _t	%	29.9
N ₃₁	m∙Hz	814
Nt	m∙Hz	1154
d ₃₁	pC/N	8
d ₃₂	pC/N	8
d ₃₃	pC/N	31
e ₃₃	mC/m ²	197
9 ₃₃	mV•m/N	450
Dielectric constants	$\varepsilon_{33}^{T}/\varepsilon_{0}$	7.8
Qm	-	25
Modulus	GPa	1.1
Specific gravity	g/cm ³	1.92

Temp. Characteristics







Temp. characteristics of resonance frequency Fr

Condition

Maintained for 1 hour at each temperature

*The value at the start of measurement is set as 100 (%).

*The values shown in this paper are for reference only and are not guaranteed. Please note that specifications are subject to change without notice for improvement.

FUJI CERAMICS CORPORATION

Head Office 2320-11 Yamamiya, Fujinomiya-shi,Shizuoka 418-0111, Japan Web: <u>https://www.fujicera.co.jp/en/</u>